

HORIZONTAL REPAIR

Master Format #: 03 01 30.71

EUCOREPAIR SCC FAST

FAST SETTING, SELF-CONSOLIDATING CONCRETE REPAIR MORTAR



EUCLID CHEMICAL

PACKAGING

50 lb (22.7 kg) bags

Code: 088FP 50

Bulk bags suitable for mixing in ready-mix trucks available (MTO)

APPROXIMATE YIELD

50 lb (22.7 kg) unit: 0.37 ft³ (0.01 m³) per unit when mixed with 4.25 pints (2.01 L) of potable water.

MINIMUM/MAXIMUM APPLICATION THICKNESS

1 inch (2.5 cm) to full depth

CLEAN UP

Clean tools and equipment with water before the material hardens.

SHELF LIFE

1 year in original, unopened package

DESCRIPTION

EUCOREPAIR SCC FAST is a fast setting, one component, cementitious, self-consolidating repair mortar that is shrinkage compensated, pozzolan and microfiber modified, and contains an integral corrosion inhibitor. It is designed for horizontal and formed vertical and overhead structural repairs in applications from 1 inch (2.5 cm) to full depth where a faster return to service is required. This material is non-metallic and non-staining.

PRODUCT CHARACTERISTICS

FEATURES/BENEFITS

- Shrinkage compensation and reduction to minimize cracking
- Pre-mixed with pea gravel, ready-to-use
- Low permeability with excellent freeze-thaw resistance
- Pozzolan and microfiber modified
- Contains an integral corrosion inhibitor
- Rapid-hardening allows user to strip forms same day
- Can be coated 5 hours after final set

COMMON METHODS

- Trowelable (horizontal applications)
- Pumpable
- Form and pour

PRIMARY APPLICATIONS

- Parking decks
- Joint repairs
- Balconies
- Equipment bases
- Pavements
- Beams
- Vertical & overhead formed repairs

TECHNICAL INFORMATION

The following are typical values obtained under laboratory conditions. Expect reasonable variation under field conditions.

Test Method	Test Property	Values
ASTM C39	Compressive Strength 3" x 6" cylinder	2 hour 2,500 psi (17 MPa) 1 day 4,500 psi (31 MPa) 7 days 6,000 psi (41 MPa) 28 days 8,000 psi (55 MPa)
ASTM C666 Procedure A	Freeze/Thaw Resistance	300 cycles . . . > 95% relative dynamic modulus
ASTM C78	Flexural Strength	1 day 500 psi (3 MPa) 7 days 900 psi (6 MPa) 28 days 1,000 psi (7 MPa)
ASTM C1202	Rapid Chloride Permeability	28 days < 300 coulombs
ASTM C157*	Length Change	28 day shrinkage < 0.020%
ASTM C1611	Slump Flow	Initial 24 - 29 inches (61-74 cm)
ASTM C1621	J-Ring Slump Flow	26.5 inches (67.3 cm) Passing Ability: 1 inch (2.5 cm) no visible blocking
	Working Time	approximately 20 - 30 minutes
ASTM C403	Set Time	Initial approximately 50 minutes
ASTM C138	Fresh Wet Density	146.0 lb/ft ³ (2338 kg/m ³)
ASTM C882 3" x 6" specimens Per TXDOT	Slant Shear Bond Strength	1 day 2,200 psi (15 MPa) 3 days 3,200 psi (22 MPa) 3 days 3,500 psi (24 MPa)
ASTM C1581	Crack Resistance	Net Time Until Cracking > 60 days Stress Rate 9.1 psi/day Potential for Cracking Low

*Based on 50% RH @ 23 °C (73 °F) (3" x 3" x 11" beam specimens were removed from molds @ 24 hours)

WARRANTY: The Euclid Chemical Company ("Euclid") solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with this warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Euclid does not authorize anyone on its behalf to make any written or oral statements which in any way alter Euclid's installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Euclid's products for the Buyer's intended purposes.

DIRECTIONS FOR USE

Surface Preparation: Concrete surfaces must be structurally sound, free of loose or deteriorated concrete and free of dust, dirt, paint, efflorescence, oil and all other contaminants. Mechanically abrade the surface to achieve a surface profile equal to CSP (Concrete Surface Profile) 5 - 7 in accordance with ICRI Guideline 310.2. Properly clean the profiled area.

Priming & Bonding (Saw Cut & Chipped Out Repairs, Form & Pour Repairs): Thoroughly clean any exposed reinforcing steel, and apply DURALPREP A.C. to the concrete and the reinforcing steel within the repair area. Refer to the DURALPREP A.C. technical data sheet for full instructions. Alternatively, application of EUCOWELD 2.0 to a dry substrate or a scrub coat of EUCOREPAIR SCC to the saturated surface dry (SSD) concrete surface may be used for bonding. The repair material must be placed on the scrub coat before the scrub coat dries out.

Formwork: For building forms, refer to ACI 347R - Guide to Formwork for Concrete. Forms should be filled with water 24 hours prior to placement of EUCOREPAIR SCC FAST to ensure tightness and adequate saturation. Ensure forms are completely drained before pouring of product and any drainage outlets are sealed.

Mixing: Single bags may be mixed with a drill and #P2, #P5, or #P6 mixing paddle according to ICRI Guideline No. 320.5. Use a horizontal shaft mortar mixer for larger jobs. All materials should be in the proper temperature range of 60 °F (15 °C) to 85 °F (29 °C). Add the appropriate amount of water for the batch size and then add the EUCOREPAIR SCC FAST. **The amount of water to be mixed with the EUCOREPAIR SCC FAST is critical. Initially add 3.5 pints [56 fl.oz.] (1.6 L) of water per 50 lb (22.7 kg) bag and mix for 2 minutes. If after the initial 2 minutes of mixing the desired flow is not obtained, no more than 0.75 pints [12 fl.oz.] (355 mL) of additional water should be added to the mix in order to achieve more flow.** Mix an additional 2 minutes after adding extra water.

Placement: IMPORTANT: The application temperature range of EUCOREPAIR SCC FAST is from 45 to 95 °F (7 to 35 °C). Allow approximately 30 minutes to mix, place, and finish EUCOREPAIR SCC FAST repair mortar at 72 °F (22 °C). To make repairs, spread with a float, come-a-long, or square tipped shovel to a thickness that is level with the surrounding concrete. Do not use EUCOREPAIR SCC FAST for repairs less than 1 inch (2.5 cm) deep. Pump or pour product immediately after mixing. Vibration is typically not required, but form vibration can be used to ensure proper consolidation in situations which restrict flowability. If vibration is used, do not vibrate in excess as this can lead to segregation of the aggregate. When placing material, refer to ACI 304R - Guide for Measuring, Mixing, Transporting, and Placing Concrete.

Finishing: Finish the repair material to the desired texture. Do not add water to the surface during the finishing operation. When placing under hot and windy conditions, the use of EUCOBAR evaporation retarder is recommended to prevent the loss of surface moisture.

Curing & Sealing: If an epoxy coating will not be applied, wet cure the surface with water and polyethylene sheets at least one day, or use a curing compound. If applying an epoxy coating, it is important to wet cure with polyethylene sheets for at least 3 hours and then allow to air dry for 2 hours before coating. EUCOREPAIR SCC FAST can be coated with epoxy 5 hours after final set at 70 °F (21 °C).

PRECAUTIONS/LIMITATIONS

- The application temperature range of EUCOREPAIR SCC FAST is 45 to 95 °F (7 to 35 °C).
- If an epoxy coating will be applied, follow surface preparation procedures as directed by the coating manufacturer.
- Do not extend with aggregate.
- Do not use as an unbonded topping.
- When necessary, follow the recommendations in ACI 305R "Guide to Hot Weather Concreting" or ACI 306R "Guide to Cold Weather Concreting".
- In all cases, consult the Safety Data Sheet before use.

Rev. 02.22

WARRANTY: The Euclid Chemical Company ("Euclid") solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with this warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Euclid does not authorize anyone on its behalf to make any written or oral statements which in any way alter Euclid's installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Euclid's products for the Buyer's intended purposes.